

(19)



(11)

EP 1 618 178 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
16.07.2008 Bulletin 2008/29

(51) Int Cl.:
A61K 35/32 (2006.01)

(21) Application number: **04749924.9**

(86) International application number:
PCT/US2004/010956

(22) Date of filing: **21.04.2004**

(87) International publication number:
WO 2004/096983 (11.11.2004 Gazette 2004/46)

(54) NOVEL GLUE FOR CARTILAGE REPAIR**NEUARTIGER KLEBSTOFF ZUR KNORPELREPARATUR****NOUVEL ADHESIF DESTINE A LA REPARATION DU CARTILAGE**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PL PT RO SE SI SK TR**

(30) Priority: **29.04.2003 US 424765**

(43) Date of publication of application:
25.01.2006 Bulletin 2006/04

(73) Proprietor: **Musculoskeletal Transplant
Foundation
Edison,
New Jersey 08837-9947 (US)**

(72) Inventors:
• **TRUNCALE, Katherine, A.
New Jersey 08844 (US)**

- **SUNWOO, Moon Hae
Old Tappan, NJ 07675 (US)**
- **GERTZMAN, Arthur, A.
Lebanon, NJ 08833 (US)**
- **TOMFORD, William, W.
Belmont, MA 02478 (US)**

(74) Representative: **McCall, John Douglas et al
W.P. THOMPSON & CO.
Coopers Building
Church Street
Liverpool L1 3AB (GB)**

(56) References cited:
**EP-A- 1 127 581 WO-A-02/058484
US-A- 5 236 456 US-A1- 2004 219 182
US-B2- 6 838 440**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 1 618 178 B1

Description

FIELD OF INVENTION

[0001] The present invention is generally directed toward an implant and is more specifically directed toward a paste or gel implant material for a cartilage defect.

BACKGROUND OF THE INVENTION

[0002] Articular cartilage injury and degeneration present medical problems to the general population which are addressed by orthopedic surgeons. Every year in the United States, over 500,000 arthroplastic or joint repair procedures are performed. These include approximately 125,000 total hip and 150,000 total knee arthroplasties and over 41,000 open arthroscopic procedures to repair cartilaginous defects of the knee.

[0003] In the knee joint, the articular cartilage tissue forms a lining which faces the joint cavity on one side and is linked to the subchondral bone plate by a narrow layer of calcified cartilage tissue on the other. Articular cartilage (hyaline cartilage) consists primarily of extracellular matrix with a sparse population of chondrocytes distributed throughout the tissue. Articular cartilage is composed of chondrocytes, type II collagen fibril network, proteoglycans and water. Active chondrocytes are unique in that they have a relatively low turnover rate and are sparsely distributed within the surrounding matrix. The collagens give the tissue its form and tensile strength and the interaction of proteoglycans with water give the tissue its stiffness to compression, resilience and durability. The hyaline cartilage provides a low friction bearing surface over the bony parts of the joint. If the lining becomes worn or damaged resulting in lesions, joint movement may be painful or severely restricted. Whereas damaged bone typically can regenerate successfully, hyaline cartilage regeneration is quite limited because of its limited regenerative and reparative abilities.

[0004] Articular cartilage lesions generally do not heal, or heal only partially under certain biological conditions due to the lack of nerves, blood vessels and a lymphatic system. The limited reparative capabilities of hyaline cartilage usually results in the generation of repair tissue that lacks the structure and biomechanical properties of normal cartilage. Generally, the healing of the defect results in a fibrocartilaginous repair tissue that lacks the structure and biomedical properties of hyaline cartilage and degrades over the course of time. Articular cartilage lesions are frequently associated with disability and with symptoms such as joint pain, locking phenomena and reduced or disturbed function. These lesions are difficult to treat because of the distinctive structure and function of hyaline cartilage. Such lesions are believed to progress to severe forms of osteoarthritis. Osteoarthritis is the leading cause of disability and impairment in middle-aged and older individuals, entailing significant economic, social and psychological costs. Each year, oste-

oarthritis accounts for as many as 39 million physician visits and more than 500,000 hospitalizations. By the year 2020, arthritis is expected to affect almost 60 million persons in the United States and to limit the activity of 11.6 million persons.

[0005] There are many current therapeutic methods being used. None of these therapies has resulted in the successful regeneration of hyaline-like tissue that withstands normal joint loading and activity over prolonged periods. Currently, the techniques most widely utilized clinically for cartilage defects and degeneration are not articular cartilage substitution procedures, but rather lavage, arthroscopic debridement, and repair stimulation. The direct transplantation of cells or tissue into a defect and the replacement of the defect with biologic or synthetic substitutions presently accounts for only a small percentage of surgical interventions. The optimum surgical goal is to replace the defects with cartilage-like substitutes so as to provide pain relief, reduce effusions and inflammation, restore function, reduce disability and postpone or alleviate the need for prosthetic replacement.

[0006] Lavage and arthroscopic debridement involve irrigation of the joint with solutions of sodium chloride, Ringer or Ringer and lactate. The temporary pain relief is believed to result from removing degenerative cartilage debris, proteolytic enzymes and inflammatory mediators. These techniques provide temporary pain relief, but have little or no potential for further healing.

[0007] Repair stimulation is conducted by means of drilling, abrasion arthroplasty or microfracture. Penetration into the subchondral bone induces bleeding and fibrin clot formation which promotes initial repair, however, the tissue formed is fibrous in nature and not durable. Pain relief is temporary as the tissue exhibits degeneration, loss of resilience, stiffness and wear characteristics over time.

[0008] The periosteum and perichondrium have been shown to contain mesenchymal progenitor cells capable of differentiation and proliferation. They have been used as grafts in both animal and human models to repair articular defects. Few patients over 40 years of age have obtained good clinical results, which most likely reflects the decreasing population of osteochondral progenitor cells with increasing age. There have also been problems with adhesion and stability of the grafts, which result in their displacement or loss from the repair site.

[0009] Transplantation of cells grown in culture provides another method of introducing a new cell population into chondral and osteochondral defects. Carticek® is a commercial process to culture a patient's own cartilage cells for use in the repair of cartilage defects in the femoral condyle marketed by Genzyme Biosurgery in the United States and Europe. The procedure uses arthroscopy to take a biopsy from a healthy, less loaded area of articular cartilage. Enzymatic digestion of the harvested tissue releases the cells that are sent to a laboratory where they are grown for a period ranging from 2-5 weeks. Once

cultivated, the cells are injected during a more open and extensive knee procedure into areas of defective cartilage where it is hoped that they will facilitate the repair of damaged tissue. An autologous periosteal flap with cambium layer is used to seal the transplanted cells in place and act as a mechanical barrier. Fibrin glue is used to seal the edges of the flap. This technique preserves the subchondral bone plate and has reported a high success rate. Proponents of this procedure report that it produces satisfactory results, including the ability to return to demanding physical activities, in more than 90% of patients and that biopsy specimens of the tissue in the graft sites show hyaline-like cartilage repair. More work is needed to assess the function and durability of the new tissue and determine whether it improves joint function and delays or prevents joint degeneration. As with the perichondrial graft, patient/donor age may compromise the success of this procedure as chondrocyte population decreases with increasing age. Disadvantages to this procedure include the need for two separate surgical procedures, potential damage to surrounding cartilage when the periosteal patch is sutured in place, the requirement of demanding microsurgical techniques, and the expensive cost of the procedure which is currently not covered by insurance.

[0010] Osteochondral transplantation or mosaicplasty involves excising all injured or unstable tissue from the articular defect and creating cylindrical holes in the base of the defect and underlying bone. These holes are filled with autologous cylindrical plugs of healthy cartilage and bone in a mosaic fashion. The osteochondral plugs are harvested from a lower weight-bearing area of lesser importance in the same joint. This technique, shown in Prior Art Figure 2, can be performed as arthroscopic or open procedures. Reports of results of osteochondral plug autografts in a small number of patients indicate that they decrease pain and improve joint function, however, long-term results have not been reported. Factors that can compromise the results include donor site morbidity, effects of joint incongruity on the opposing surface of the donor site, damage to the chondrocytes at the articular margins of the donor and recipient sites during preparation and implantation, and collapse or settling of the graft over time. The limited availability of sites for harvest of osteochondral autografts restricts the use of this approach to treatment of relatively small articular defects and the healing of the chondral portion of the autograft to the adjacent articular cartilage remains a concern.

[0011] Transplantation of large allografts of bone and overlying articular cartilage is another treatment option that involves a greater area than is suitable for autologous cylindrical plugs, as well as for a non-contained defect. The advantages of osteochondral allografts are the potential to restore the anatomic contour of the joint, lack of morbidity related to graft harvesting, greater availability than autografts and the ability to prepare allografts in any size to reconstruct large defects. Clinical experience with fresh and frozen osteochondral allografts shows that

these grafts can decrease joint pain, and that the osseous portion of an allograft can heal to the host bone and the chondral portion can function as an articular surface. Drawbacks associated with this methodology in the clinical situation include the scarcity of fresh donor material and problems connected with the handling and storage of frozen tissue. Fresh allografts carry the risk of immune response or disease transmission. Musculoskeletal Transplant Foundation (MTF) has preserved fresh allografts in a media that maintains a cell viability of 50% for 35 days for use as implants. Frozen allografts lack cell viability and have shown a decreased amount of proteoglycan content which contribute to deterioration of the tissue.

[0012] A number of patents in the prior art show the use of bone putty, pastes or gels to fill bone defects. U.S. Patent Number 5,290,558 issued March 1, 1994 discloses a flowable demineralized bone powder composition using an osteogenic bone powder with large particle size ranging from about 0.1 to about 1.2 cm. mixed with a low molecular weight polyhydroxy compound possessing from 2 to about 18 carbons including a number of classes of different compounds such as monosaccharides, disaccharides, water dispersible oligosaccharides and polysaccharides.

[0013] A bone gel is disclosed in the U.S. Patent Number 5,073,373 issued December 17, 1991. Bone lamellae in the shape of threads or filaments retaining low molecular weight glycerol carrier are disclosed in U.S. Patent Numbers 5,314,476 issued May 24, 1994 and 5,507,813 issued April 16, 1996 and the tissue forms described in these patents are known commercially as the GRAFTON® Putty and Flex, respectively.

[0014] U.S. Patent Number 5,356,629 issued October 18, 1994 discloses making a rigid gel in the nature of a bone cement to fill defects in bone by mixing biocompatible particles, preferably polymethylmethacrylate coated with polyhydroxyethylmethacrylate in a matrix selected from a group which lists hyaluronic acid to obtain a molded semi-solid mass which can be suitably worked for implantation into bone. The hyaluronic acid can also be utilized in monomeric form or in polymeric form preferably having a molecular weight not greater than about one million Daltons. It is noted that the nonbioabsorbable material which can be used to form the biocompatible particles can be derived from xenograft bone, homologous bone, autogenous bone as well as other materials. The bioactive substance can also be an osteogenic agent such as demineralized bone powder, morselized cancellous bone, aspirated bone marrow and other autogenous bone sources. The average size of the particles employed is preferably about 0.1 to about 3.0 mm, more preferably about 0.2 to about 1.5 mm, and most preferably about 0.3 to about 1.0 mm. It is inferentially mentioned but not taught that particles having average sizes of about 7,000 to 8,000 microns, or even as small as about 100 to 700 microns can be used.

[0015] U.S. Patent Number 4,172,128 issued October

23, 1979 discloses a demineralized bone material mixed with a carrier to reconstruct tooth or bone material by adding a mucopolysaccharide to a mineralized bone colloidal material. The composition is formed from a demineralized coarsely ground bone material, which may be derived from human bones and teeth, dissolved in a solvent forming a colloidal solution to which is added a physiologically inert polyhydroxy compound such as mucopolysaccharide or polyuronic acid in an amount which causes orientation when hydrogen ions or polyvalent metal ions are added to form a gel. The gel will be flowable at elevated temperatures above 35° C and will solidify when brought down to body temperature. Example 25 of the patent notes that mucopolysaccharides produce pronounced ionotropic effects and that hyaluronic acid is particularly responsible for spatial cross-linking.

[0016] U.S. Patent Number 6,030,635 issued February 29, 2000 and U.S. Patent Number 6,437,018 issued August 20, 2002 are directed toward a malleable bone putty and a flowable gel composition for application to a bone defect site to promote new bone growth at the site which utilize a new bone growth inducing compound of demineralized lyophilized allograft bone powder. The bone powder has a particle size ranging from about 100 to about 850 microns and is mixed in a high molecular weight hydrogel carrier which contains a sodium phosphate saline buffer.

[0017] The use of implants for cartilage defects is much more limited. Aside from the fresh allograft implants and autologous implants, U.S. Patent Number 6,110,209 issued November 5, 1998 shows the use an autologous articular cartilage cancellous bone paste to fill arthritic defects. The surgical technique is arthroscopic and includes debriding (shaving away loose or fragmented articular cartilage), followed by morselizing the base of the arthritic defect with an awl until bleeding occurs. An osteochondral graft is then harvested from the inner rim of the intercondylar notch using a trephine. The graft is then morselized in a bone graft crusher, mixing the articular cartilage with the cancellous bone. The paste is then pushed into the defect and secured by the adhesive properties of the bleeding bone. The paste can also be mixed with a cartilage stimulating factor, a plurality of cells, or a biological glue. All patients are kept non-weight bearing for four weeks and used a continuous passive motion machine for six hours each night. Histologic appearance of the biopsies have mainly shown a mixture of fibrocartilage with hyaline cartilage. Concerns associated with this method are harvest site morbidity and availability, similar to the mosaicplasty method.

SUMMARY OF THE INVENTION

[0018] A cartilage implant material in paste or gel form for repairing articular cartilage defects is composed of milled allograft cartilage pieces in a bioabsorbable carrier. Autologous chondrocyte in an amount exceeding the number naturally occurring in hyaline cartilage for a ma-

ture adult between 20 and 55 years of age may also be applied to the matrix. Additives may be applied to the mixture in order to increase chondrocyte migration and proliferation. The implant material can support the addition of a variety of chondrogenic stimulating factors including, but not limited to growth factors (FGF-2, FGF-5, IGF-1, TGF- β , BMP-2, BMP-7, PDGF, VEGF), human allogenic or autologous chondrocytes, human allogenic or autologous bone marrow cells, stem cells, demineralized bone matrix, insulin, insulin-like growth factor-1, transforming growth factor-B, interleukin-1 receptor antagonist, hepatocyte growth factor, platelet-derived growth factor, Indian hedgehog and parathyroid hormone-related peptide or bioactive glue.

[0019] The implant material is placed in the lesion area and may be sealed with a periosteum cap.

[0020] It is an object of the invention to provide an allograft implant material for joints which provides pain relief, restores normal function and will postpone or alleviate the need for prosthetic replacement.

[0021] It is also an object of the invention to provide a cartilage repair implant material which is easily placed in a defect area by the surgeon using an arthroscopic, minimally invasive technique.

[0022] It is further an object of the invention to provide an allograft implant material procedure which is applicable for both partial and full thickness lesions.

[0023] It is yet another object of the invention to provide an allograft implant material which facilitates growth of hyaline cartilage.

[0024] It is an additional object of the invention to provide implant paste and gel material formulations that satisfy surgical requirements and are made from donated human available allograft tissue, some of which would otherwise be considered waste and thrown away.

[0025] These and other objects, advantages, and novel features of the present invention will become apparent when considered with the teachings contained in the detailed disclosure along with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0026]

Figure 1 shows the anatomy of a knee joint with a lesion;

Figure 2 shows a schematic mosaicplasty as known in the prior art; and

Figure 3 shows a schematic perspective view of cartilage defect material placed in a defect site with an exploded periosteum cap.

DESCRIPTION OF THE INVENTION

[0027] The terms "tissue" is used in the general sense herein to mean any transplantable or implantable tissue, the survivability of which is improved by the methods described herein upon implantation. In particular, the overall

durability and longevity of the implant are improved, and host-immune system mediated responses, are substantially eliminated.

[0028] The terms "transplant" and "implant" are used interchangeably to refer to tissue, material or cells (xenogeneic or allogeneic) which may be introduced into the body of a patient to replace or supplement the structure or function of the endogenous tissue.

[0029] The terms "autologous" and "autograft" refer to tissue or cells which originate with or are derived from the recipient, whereas the terms "allogeneic" and "allograft" refer to cells and tissue which originate with or are derived from a donor of the same species as the recipient. The terms "xenogeneic" and "xenograft" refer to cells or tissue which originates with or is derived from a species other than that of the recipient.

[0030] The term "gel" refers to a mixture of minced or milled pretreated allograft cartilage in a biocomposite carrier having a viscosity which is less than and is less rigid than a mixture of minced or milled pretreated allograft cartilage in a biocompatible carrier referred to by the terms "putty" or "paste" and contains less cartilage by weight than putty or paste.

[0031] The present invention is directed towards a cartilage repair material and method of treatment. The preferred embodiment and best mode of the invention is shown in Figure 3. In the production of the invention, allograft hyaline cartilage is lyophilized reducing its water content and milled for ease in application.

[0032] After washes with sterile de-ionized (DI) water, the cartilage material was frozen at -20° to -100° C preferably -70° C and lyophilized to reduce the water content within the range of about 0.1% to about 8.0%. The cartilage is frozen with liquid nitrogen and ground into particles.

[0033] A lesion or defect is removed by cutting a bore 50 or trimming a lesion in the implant area 100 and filling the bore 50 or lesion area with a milled cartilage mixture 20 of paste or gel consisting together with a biological carrier such as hyaluronic acid and its derivatives, gelatin, collagen, chitosan, alginate, buffered PBS, Dextran, or polymers and one or more additives namely chondrogenic stimulating factors including, but not limited to growth factors (FGF-2, FGF-5, IGF-1, TGF- β , BMP-2, BMP-7, PDGF, VEGF), human allogenic or autologous chondrocytes, human allogenic cells, human allogenic or autologous bone marrow cells, human allogenic or autologous stem cells, demineralized bone matrix, insulin, insulin-like growth factor-1, interleukin-1 receptor antagonist, hepatocyte growth factor, platelet-derived growth factor, Indian hedgehog and parathyroid hormone-related peptide.

[0034] Suitable organic glue material can be used to keep the viscous cartilage mixture 20 fixed in place in the implant area or to affix a periosteal cap 30 in place over the surrounding hyaline cartilage area 100. Suitable organic glue material can be found commercially, such as for example; TISSEEL® or TISSUCOL® (fibrin based

adhesive; Immuno AG, Austria), Adhesive Protein (Sigma Chemical, USA), and Dow Coming Medical Adhesive B (Dow Corning, USA).

[0035] Example 1: A matrix of minced cartilage putty consisting of minced or milled allograft articular cartilage which has been lyophilized so that its water content ranges from 0.1 % to 8.0% with a cartilage content ranging from 25% to 50% by weight is mixed with a carrier of sodium hyaluronate solution (HA) (molecular weight ranging from 7.0×10^5 to 1.2×10^6) or any other bioabsorbable carrier such as hyaluronic acid and its derivatives, gelatin, collagen, chitosan, alginate, buffered PBS, Dextran, or polymers, the carrier ranging from 75% to 50% by weight. The cartilage is milled to a size ranging from 0.01mm to 1 mm. In gel form, the minced cartilage which has been lyophilized so that its water content ranges from 0.1% to 8.0% ranging from 15% to 30% by weight and the carrier ranges from 85% to 70% by weight. The particle size of the cartilage when milled is less than or equal to 1 mm dry in the previously stated range. The cartilage pieces can be processed to varying particle sizes and the HA or other carrier can have different viscosities depending on the desired consistency of the putty or paste. This cartilage matrix can be deposited into the cartilage defect arthroscopically and fit into the defect where it is held in place by it's own viscosity, mixed with fibrin glue or covered with a periosteal or perichondrial flap, then sealed with biological glue. As with the first two matrices, this matrix can support the previously mentioned chondrogenic factors.

[0036] Example 2: A matrix of minced cartilage putty consisting of minced or milled allograft cartilage which has been lyophilized so that its water content ranges from 0.1 % to 8.0% ranging from 25% to 50% by weight is mixed with a carrier of sodium hyaluronate solution (HA) (7.0×10^5 to 1.2×10^6) or any other bioabsorbable carrier such as hyaluronic acid and its derivatives, gelatin, collagen, chitosan, alginate, buffered PBS, Dextran, or polymers ranging from 75% to 50% by weight. In a gel form, the minced cartilage which has been lyophilized so that its water content ranges from 0.01% to 8.0% ranging from 15% to 30% by weight and the carrier ranges from 85% to 70% by weight. The particle size of the cartilage is less than or equal to 1 mm dry ranging from 0.01mm to 1mm. The cartilage pieces can be processed to varying particle sizes and the HA or carrier can have different viscosities depending on the desired consistency of the putty or paste. Autologous or allogenic cells which have been grown outside the patient are inserted by syringe into the matrix before, during or after deposit of the cartilage matrix into the defect area. Such cells include allogenic or autologous bone marrow cells, stem cells and chondrocyte cells. The cellular density of the cells preferably ranges from about 1×10^8 to 5×10^8 or from about 100 million to about 500 million cells per cc of putty or gel mixture. This composite material can be injected into the cartilage defect arthroscopically and fit into the defect where it is held in place by it's own viscosity, or covered with a pe-

riosteal or perichondrial flap, then sealed with biological glue. As with the first matrix, this matrix can support the previously mentioned chondrogenic factors.

[0037] The operation of placing the cartilage composition in a cartilage defect, comprises (a) cutting a patient's tissue at a site of a cartilage defect to remove the diseased area of cartilage; (b) placing a mixture of milled allograft cartilage in a bioabsorbable carrier in the defect area; and (c) placing a periosteal cover over the mixture of the inserted milled allograft cartilage in a bioabsorbable carrier to contain the mixture in the defect area for a predetermined period of time to promote cartilage growth at the defect site. Alternate steps include the addition of growth factors, chondrocytes, bone marrow cells and stem cells.

Claims

1. A sterile allograft cartilage defect implant material for use in human beings comprising milled allograft cartilage pieces sized less than 1 mm lyophilized so that their water content ranges from about 0.1% to about 8.0% in a bioabsorbable carrier.
2. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said milled cartilage ranges from about 25% to about 50% by weight and said carrier ranges from about 75% to about 50% by weight.
3. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said milled cartilage ranges from about 15% to about 30% by weight with the carrier ranging from about 85% to about 70% by weight.
4. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said carrier is sodium hyaluronate and its derivatives.
5. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said implant material includes a protein glue.
6. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said implant material includes the addition of autologous chondrocytes to achieve a concentration exceeding the concentration of chondrocytes naturally occurring in the patient.
7. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said milled cartilage is taken from a group consisting of one or more of hyaline cartilage and fibrous cartilage.
8. A sterile allograft cartilage defect implant material as

claimed in claim 1 including an additive to said implant material consisting of one or more of a group consisting of growth factors taken from a group consisting of FGF-2, FGF-5, IGF-1, TGF- β , BMP-2, BMP-7, PDGF, VEGF, human allogenic cells, human allogenic bone marrow cells, human autologous bone marrow cells, human allogenic stem cells, human autologous stem cells, human demineralized bone matrix, and insulin.

9. A sterile allograft cartilage defect implant material as claimed in claim 1 wherein said milled allograft articular cartilage pieces range from 0.01 mm to 1.0 mm in size and said bioabsorbable carrier taken from a group consisting of sodium hyaluronic, hyaluronic acid and its derivatives, gelatin, collagen, chitosan, alginate, buffered PBS, Dextran or polymers and allogenic chondrocytes in an amount exceeding the natural occurrence of same in articular cartilage.
10. A sterile allograft cartilage defect material as claimed in claim 1, wherein said implant material has bone marrow cells in an amount exceeding the natural occurrence of same in a patient being treated.
11. A sterile allograft cartilage defect implant material as claimed in claim 1, wherein said implant material includes the addition of allogenic chondrocytes in an amount exceeding the natural occurrence of same in a patient being treated.

Patentansprüche

1. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte zur Verwendung in Menschen, das gemahlene Allotransplantat-Knorpelstücke von einer Größe kleiner als 1 mm, die lyophilisiert sind, sodass ihr Wassergehalt von etwa 0,1 % bis etwa 8,0 % reicht, in einem bioabsorbierbaren Träger umfasst.
2. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genannter gemahlener Knorpel von etwa 25 Gewichts-% bis etwa 50 Gewichts-% reicht und genannter Träger von etwa 75 Gewichts-% bis etwa 50 Gewichts-% reicht.
3. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genannter gemahlener Knorpel von etwa 15 Gewichts-% bis etwa 30 Gewichts-% reicht, wobei der Träger von etwa 85 Gewichts-% bis etwa 70 Gewichts-% reicht.
4. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genannter Träger Natriumhyaluronat und seine Derivate darstellt.
5. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin das Implantatmaterial ein Proteinkleber enthält.

peldefekte nach Anspruch 1, worin genanntes Implantatmaterial einen Proteinleim einschließt.

6. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genanntes Implantatmaterial die Zugabe von autologen Chondrozyten einschließt, um eine Konzentration zu erreichen, die die im Patienten natürlich vorkommende Konzentration von Chondrozyten übersteigt. 5
7. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genannter gemahlener Knorpel aus einer Gruppe entnommen wird, die aus einem oder mehreren von hyalinem Knorpel und Faserknorpel besteht. 10
8. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, das einen Zusatz zu genanntem Implantatmaterial einschließt, der aus einem oder mehreren einer Gruppe besteht, die aus Wachstumsfaktoren besteht, die einer Gruppe entnommen sind, die aus Folgenden besteht: FGF-2, FGF-5, IGF-1, TGF- β , BMP-2, BMP-7, PDGF, VEGF, menschlichen allo genen Zellen, menschlichen allo genen Knochenmarkzellen, menschlichen autologen Knochenmarkzellen, menschlichen allo genen Stammzellen, menschlichen autologen Stammzellen, menschlicher demineralisierter Knochenmatrix und Insulin. 15
9. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genannte gemahlene, artikuläre Allotransplantat-Knorpelstücke von 0,01 mm bis 1,0 mm Größe reichen und genannter bioabsorbierbarer Träger aus einer Gruppe entnommen ist, die aus Folgenden besteht: Natriumhyaluronat, Hyaluronsäure und seine Derivate, Gelatine, Kollagen, Chitosan, Alginat, gepuffertem PBS, Dextran oder Polymeren, und allogene Chondrozyten in einer Menge das natürliche Vorkommen der Gleichen in artikulärem Knorpel übersteigen. 20
10. Steriles Allotransplantat-Material für Knorpeldefekte nach Anspruch 1, worin genanntes Implantatmaterial Knochenmarkzellen in einer Menge enthält, die das natürliche Vorkommen der Gleichen in einem Patienten, der behandelt wird, übersteigt. 25
11. Steriles Allotransplantat-Implantatmaterial für Knorpeldefekte nach Anspruch 1, worin genanntes Implantatmaterial die Zugabe von allo genen Chondrozyten in einer Menge einschließt, die das natürliche Vorkommen der Gleichen in einem Patienten, der behandelt wird, übersteigt. 30

Revendications

1. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux destiné à être utilisé chez les être humains qui comprend des morceaux de cartilage d'allogreffe broyés d'une taille inférieure à 1 mm lyophilisés de sorte que leur teneur en eau varie d'environ 0,1 % à environ 8,0 % dans un véhicule bioabsorbable. 5
2. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit cartilage broyé représente d'environ 25 % à environ 50 % en poids et ledit véhicule représente d'environ 75 % à environ 50 % en poids. 10
3. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit cartilage broyé représente d'environ 15 % à environ 30 % en poids, le véhicule représentant d'environ 85 % à environ 70 % en poids. 15
4. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit véhicule est l'hyaluronate de sodium et ses dérivés. 20
5. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit matériau d'implant inclut une colle protéique. 25
6. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit matériau d'implant inclut l'ajout de chondrocytes autologues pour atteindre une concentration dépassant la concentration de chondrocytes présente naturellement chez le patient. 30
7. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit cartilage broyé est pris dans un groupe constitué par un ou plusieurs cartilages d'un cartilage hyalin et d'un cartilage fibreux. 35
8. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 qui inclut un additif au dit matériau d'implant constitué par un ou plusieurs éléments d'un groupe constitué par les facteurs de croissance pris dans un groupe constitué par le FGF-2, le FGF-5, l'IGF-1, le TGF- β , la BMP-2, la BMP-7, le PDGF et le VEGF ; et les cellules allogènes humaines, les cellules de moelle osseuse allogènes humaines, les cellules de moelle osseuse autologues humaines, les cellules souches allogènes humaines, les cellules souches autologues humaines, une matrice osseuse déminéralisée humaine et l'insuline. 40

9. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel lesdits morceaux de cartilage articulaire d'allogreffe broyés ont une taille allant de 0,01 mm à 1,0 mm et ledit véhicule bioabsorbable est pris dans un groupe 5
constitué par l'hyaluronate de sodium, l'acide hyaluronique et ses dérivés, la gélatine, le collagène, la chitosane, un alginat, un tampon de PBS, le dextran ou des polymères et les chondrocytes allogènes présents en une quantité dépassant l'occurrence naturelle de ceux-ci dans le cartilage articulaire. 10
10. Matériau stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit matériau d'implant comporte des cellules de moelle osseuse 15
en une quantité dépassant l'occurrence naturelle de celles-ci chez un patient en cours de traitement.
11. Matériau d'implant stérile d'allogreffe pour défaut cartilagineux selon la revendication 1 dans lequel ledit matériau d'implant inclut l'ajout de chondrocytes allogènes en une quantité dépassant l'occurrence naturelle de ceux-ci chez un patient en cours de traitement. 20
- 25
- 30
- 35
- 40
- 45
- 50
- 55




Fig. 1




Fig. 2




Fig. 3

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 5290558 A [0012]
- US 5073373 A [0013]
- US 5314476 A [0013]
- US 5507813 A [0013]
- US 5356629 A [0014]
- US 4172128 A [0015]
- US 6030635 A [0016]
- US 6437018 B [0016]
- US 6110209 A [0017]